fictiv

NYLON 11 FR 3DP MATERIAL SPECIFICATIONS

About

Nylon-based material with fire retardant properties, used in applications where flame resistance is essential.

Applications

- Heat resistant
- Strong

| TYPICAL PHYSICAL PROPERTIES | |
|---|--------------------------|
| PROPERTIES | VALUE |
| Maximum Build Size (X, Y, Z mm) | 700 x 380 x 580 mm |
| Resolution | 0.1 mm |
| Tensile strength (XY, XZ, ZX) | 46 MPa XY, 39 MPa ZX |
| Elastic Modulus (MPa) | 1586 MPa XY / 448 MPa ZX |
| HDT (Heat Deflection Temp) °C @ 1.80 MPa | n/a |
| HDT°C @ 0.45 MPa | n/a |

The information presented represents typical values intended for reference and comparison purposes only. It should not be used for design specifications or quality control purposes. End-use material performance can be impacted (+/-) by, but not limited to, part design, end-use conditions, test conditions, color etc. Actual values will vary with build conditions. Product specifications are subject to change without notice. The performance characteristics of these materials may vary according to application, operating conditions, or end use. Each user is responsible for determining that the material is safe, lawful, and technically suitable for the intended application. Stratasys makes no warranties of any kind, express or implied, including, but not limited to, the warranties of merchantability, fitness for a particular use, or warranty against patent infringement.

XZ = X or "on edge" XY = Y or "flat" ZX = Z or "upright"

fictiv

Custom Manufacturing Made Simple.

B X O

168 Welsh St., San Francisco, CA 94107 help@fictiv.com (415) 580-2509