fictiv

PA 12 GLASS BEADS

3DP MATERIAL SPECIFICATIONS

About

MJF PA12 Glass Bead combines the strength of nylon with glass bead reinforcement, providing enhanced stiffness and dimensional stability for parts that require higher rigidity.

Applications

- Strong
- Smooth

TYPICAL PHYSICAL PROPERTIES	
PROPERTIES	VALUE
Maximum Build Size (X, Y, Z mm)	380 x 284 x 380 mm
Resolution	0.08 mm
Tensile strength (XY, XZ, ZX)	30 MPa / 4352 PSI
Elastic Modulus (MPa)	
HDT (Heat Deflection Temp)	175°C / 347°F @ 0.45 MPa

The information presented represents typical values intended for reference and comparison purposes only. It should not be used for design specifications or quality control purposes. End-use material performance can be impacted (+/-) by, but not limited to, part design, end-use conditions, test conditions, color etc. Actual values will vary with build conditions. Product specifications are subject to change without notice. The performance characteristics of these materials may vary according to application, operating conditions, or end use. Each user is responsible for determining that the material is safe, lawful, and technically suitable for the intended application. Stratasys makes no warranties of any kind, express or implied, including, but not limited to, the warranties of merchantability, fitness for a particular use, or warranty against patent infringement.

XZ = X or "on edge" XY = Y or "flat" ZX = Z or "upright"

fictiv

Custom Manufacturing Made Simple.

B X O

168 Welsh St., San Francisco, CA 94107 help@fictiv.com | (415) 580-2509